

TYTRO® SA 530

Alkali-free, liquid, high-performance set accelerator for shotcrete

Product Description

TYTRO® SA 530 is a high-performance, alkali-free set accelerator specifically formulated to provide high early strength at low dosage rates, and improve productivity by shortening the time of setting without compromising long-term strength and durability.

TYTRO SA 530 is an easy flow, ready-to-use, non-alkali and is formulated to comply with the requirements ASTM C 1141/C 1141M, Types I/II, Grade 9, Class A.

Uses

TYTRO SA 530 is used in all shotcrete applications where high early strength is required, and especially in the following applications:

- Temporary and permanent rock support in tunnels
- Underground rock support in mining
- Slope stabilisation

Product Advantages

- Efficient dosage rate – highly active formulation for lowest dosages
- Reduced excavation downtime – increased adhesion and faster setting
- Improved strength – increased early age strength development without compromising later age strength
- Reduced cycle times – quicker setting action and increased layer thickness for overhead work
- Minimum material waste – lower rebound and dust
- Safer and healthier to handle – non-alkaline formulation
- Robust and easy to formulate – liquid product, easily measured and dosed

Addition Rates

The dosage of TYTRO SA 530 can vary based on the type of application, mix design, cement type and content, water-to-cementitious materials ratio, temperature of the concrete, ambient temperature and temperature of the substrate on which the concrete is to be applied.

The dosage of TYTRO SA 530 normally ranges between 4% and 8% by the total weight of cementitious materials. Overdosing (>10%)

may result in decreased final strength. Should conditions require using more than the recommended addition rates, please consult your local GCP representative.

GCP recommends that trials be performed before use to assess and optimise dosage rates and shotcrete performance. Pre-determined and tested re-entry requirements are to be measured and nominated. If further assistance is required please consult your local GCP representative.

Mixing

TYTRO SA 530 is added at the nozzle. TYTRO SA 530 is a suspension and therefore not all types of dosing pumps will work properly. Advice on dosing pumps is available from GCP on request.

Packaging

TYTRO SA 530 is available in 205L polyethylene drums and 1,000L totes. TYTRO SA 530 is also available in bulk, delivered by metred tank trucks on request.

Storage

Temperature

TYTRO SA 530 should be stored at a temperature range of 5°C to 35°C. It is recommended that TYTRO SA 530 be kept out of direct sunlight.

Conditions

TYTRO SA 530 must be kept in closed plastic containers or closed tanks made of polyethylene or PVC. Do not store in steel containers as the pH can cause corrosion which might affect the performance of the product. Containers must be tightly closed every day to avoid contact with air which can cause a chemical reaction (skin building on top and lumps which cause problems with dosing pumps).

After prolonged storage, TYTRO SA 530 should be vigorously recirculated in the tanks by means of stirring apparatus or through recirculation before use. It can have a settlement that may not be visually detectable.

Properties

Form	Liquid
Colour	Yellow
Density (g / cm ³)	1.46 ± 0.02
pH (25°C)	3 +/- 1
Chloride content	<0.1%
Thermal stability	5°C to 35°C

Shelf life

Shelf life is 3 months. Depending on storage conditions, the shelf life may be greater than stated. Please contact your local GCP representative regarding the suitability for use if the shelf life of TYTRO SA 530 has been exceeded.

Health and Safety

Avoid eye and skin contact and wear rubber gloves and goggles. If contact occurs, rinse with plenty of water. In case of eye contact,

seek medical advice. For further information, refer to the Material Safety Data Sheet or contact your local GCP representative.

Compatibility

TYTRO SA 530 is compatible with all TYTRO shotcrete admixtures. GCP recommends that a suitable superplasticiser and slump life controlling admixture be incorporated into the shotcrete mix to achieve extended working life and maintain low water-to-cementitious materials ratio. TYTRO WR high range water-reducing and TYTRO HC hydration control admixtures are recommended for this purpose.

Pretesting of the shotcrete mix should be performed before use and as conditions and materials change in order to ensure compatibility with other admixtures.

For use with other shotcrete admixtures systems, we recommend you to contact GCP Applied Technologies for further advice.

gcpat.com | For technical information: asia.enq@gcpat.com

Australia 1800 855 525 New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898
India: Chennai +91 44 6624 2308 Delhi +91 124 402 8923 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800
Malaysia +60 3 9074 6133 Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

TYTRO is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

Printed in Singapore | 03/16 | 200-TYTRO-261



gcp applied technologies