

ADVA[®] Cast DC 600

High early strength superplasticiser

Product Description

ADVA[®]Cast DC 600 is a polycarboxylic high range water-reducing admixture that is specially designed for producing superior high early strength concrete in precast applications. ADVA[®]Cast DC 600 has been designed for concrete that is made with very low water/cement ratios, i.e. Dry-cast Concrete. ADVA[®]Cast DC 600 contains no added chloride. It is formulated to comply with specifications for chemical admixtures for concrete: AS 1478 as a Type HWR.

One litre weighs approximately 1.060kg ± 0.02kg.

Product Advantages

- Superior early strength enhancement
- Slump retention
- High workability
- Superior surface finish
- Superior water reduction
- Optimise precast concrete production

Advantages

Superior Early Strength Enhancement

ADVA[®]Cast DC 600 accelerates cement hydration at a very early stage. Together with the very efficient dispersion effect, ADVA[®]Cast DC 600 achieves very high early strength for the production of precast structural elements.

Superior Surface Finish

ADVA[®]Cast DC 600 produces concrete with superior surface finish, without stickiness, tearing or spotty set characteristics.

High Workability

ADVA[®]Cast DC 600 is ideal for precast applications, where high early strength is desired, and where high workability will aid faster placement and improved mix consolidation.

Superior Water Reduction

With up to 30% water reduction possible, ADVA[®]Cast DC 600 is highly effective in low water-cement concrete, producing high early strength concrete.

Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

Packaging

ADVA®Cast DC 600 is available in bulk.

ADVA®Cast DC 600 contains no flammable ingredients. It will begin to freeze at approximately 0°C, but will return to full strength after thawing and thorough agitation.

In storage, and for proper dispensing, ADVA®Cast DC 600 should be maintained at temperatures above 0°C.

Uses

ADVA®Cast DC 600 produces concrete with high early strength for precast structural elements, while at the same time achieving high workability for easy and fast placement and consolidation. It also allows concrete to be produced with very low water-cement ratios in low to high slump ranges. Ideally suited for Dry-cast concrete.

Optimise Precast Concrete Production

The accelerated set times of ADVA®Cast DC 600 may eliminate or minimise the need for heat curing to achieve high early strength concrete. The earlier removal of forms leads to reduced cycle times, faster mould turnaround, reduced costs and increased productivity.

Addition Rates

Addition rates of ADVA®Cast DC 600 can vary with type of applications, but will normally range from 300 to 1,000mL / 100kg of cementitious material. In most instances, the addition of 400 to 800mL / 100kg of cementitious material will be sufficient. Should conditions require using more than recommended addition rates, please consult your local GCP representative.

Compatibility

ADVA®Cast DC 600 is compatible with most water-reducing admixtures as well as specialty admixtures like accelerators, DCI® Corrosion Inhibitor, ECLIPSE® Shrinkage-Reducing Admixture and V-MAR® Rheology-Modifying Admixture.

However, it cannot be used in conjunction with DAREX® Super 20 or DARACEM®. All admixtures should be separately added to the concrete. Pretesting of the concrete should be performed to optimise dosages and addition sequence of these admixtures.

Health and Safety

Read and understand the product label and Safety Data Sheet (SDS) if handling the product directly. All users should acquaint themselves with this information prior to working with the product and follow the precautionary statements. SDSs can be obtained by contacting your local GCP representative or office.

gcpat.com.au | Australia customer service: 1800 855 525

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ADVA, DCI, ECLIPSE, V-MAR, DAREX and DARACEM are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2021 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com.au. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2021-09-22

gcpat.com.au/solutions/products/adva-cast-high-range-admixtures/adva-cast-dc-600