

# CHEMBOND™

High performance latex modifier for cement

---

## Product Description

CHEMBOND™ is a synthetic latex which, when added to adhesives, mortar and concrete mixes, enhances their basic properties. The cured compound has exceptional adhesion to brick, concrete, ceramic tiles and to most other building materials such as timber, many metals, expanded polystyrene foam and rigid polyurethane foam. CHEMBOND™ increases flexural strength.

## Product Uses

CHEMBOND™ is used to repair or patch cementitious, brick and other appropriate substrates before the installation of GCP waterproof membrane systems. It is used to produce premium quality, high performance polymer modified cement mixes for external or internal applications including:

- Adhesive binder for render systems
- Adhesion slurry coat over Aquagard M polyurethane membranes
- Repair of concrete and masonry
- Thin topping or levelling screeds
- Moisture proof sealer for concrete, render, FC and CFC
- Bonding agent for CRYSTALSEAL™ slurry
- Waterproof grouts and render coatings

## Product Advantages

- No toxic or hazardous ingredients
- Water clean-up
- Resists spalling – moves with substrate
- Boosts tensile and compressive strength
- Increases flexural and adhesive strength
- Resists acids, alkalis and fats
- Excellent exterior durability
- Totally waterproof
- Multi-purpose and easy to use
- Single pack
- Economical with high performance
- Systems for Total Project Specification

## Preparation

All surfaces must be sound, smooth, dry and free from dust, debris, oil or other contaminants. Bony concrete should be removed. Any exposed steel and porous or very smooth surfaces should be first carefully cleaned and then sealed with a slurry of CHEMBOND™:Water:Cement:Sand in the ratio of 1:1:2:1 applied by short bristled brush. Fine sand may be deleted depending on surface finish required. Porous concrete may be dampened prior to applying slurry.

Note: Application to porous substrates at elevated temperatures or in windy conditions may result in trowelling difficulties, poor surface adhesion and fine shrinkage cracking

## Application

- **Renders**
  - Do not exceed 7 mm per coat. Thicker layer may cause sagging or separation from wet primer coat.
  - Scratch surface of each coat and leave for at least 6 hours before applying further coats.
  - Trowel final coat to required finish.
- **Floor Toppings**
  - Toppings based on CHEMBOND™ can be laid to any thickness (12 mm min.) depending on the sieve grading of the sand.
  - Feather edging is permissible for non-critical areas but use of 24 hr damp curing is particularly important.
- **Trowelling**
  - Use semi-dry mix – consistency must allow total compaction by methods used.
  - CHEMBOND mortar should be placed on wet priming coat, then levelled, well compacted and floated smooth – finish as required.
  - Thick toppings (>50 mm) do not require CHEMBOND additive, place topping directly onto wet CHEMBOND priming coat.

## Special Use Mix Ratio

- **Moisture Sealer** – Dilute with equal parts of water and apply 1 or 2 coats 5–6m<sup>2</sup>/litre by brush or roller.
- **Waterproof Render** – Dilute CHEMBOND™ with 2 parts water and add to dry cement blend mix.
- **CRYSTALSEAL™ Waterproofing** – Mix 5 parts water to CHEMBOND – add to CrystalSeal powder to obtain required consistency.

## Concrete, Mortar & Render Mix Design

- Quantity of CHEMBOND™ diluted with 5 parts of water required for 1m<sup>3</sup> in:
- Standard Concrete – 160 – 170 litres
- Mortar/Screed – 200 litres
- Concrete Patching and Repair Mortar – 1 pbw cement to 3 pbw sand – add CHEMBOND/water 1 : 1 mix, to achieve required consistency.
- Topping < 10mm thick – 1 pbw cement to 2 pbw sand – add CHEMBOND/water 1 : 1 mix, to achieve required consistency.

- Topping < 20mm thick – 1 pbw cement to 5 pbw sharp sand – add CHEMBOND™/water 1 : 5 mix, to achieve required consistency.
- Key coat for Aquagard M PU waterproof membrane – Mix slurry of CHEMBOND™:Water:Cement:Sand in ratio 1:1:1:1 and apply with stiff bristle brush.
- Bagging render/texture – 1 pbw cement: 4 parts fine sand – add CHEMBOND™/water 1 : 2 mix, to required slurry consistency.

## Packaging

CHEMBOND™ packed in 20 litre pails or 200 litre drums.

## Clean up

Clean with water before final cure occurs. MULTITEK™ XYLENE may assist with the removal of partially cured product. Exercise care when using solvents. Please review all MSDS before use. Release Date: 02/11/18. The information contained in this product data sheet supersedes all previous versions.

## Shelf Life

Unopened or resealed pails of CHEMBOND will have a shelf life of 2 years, when stored in a dry, cool place. Protect from frost.

PROPERTY	CHEMBOND	CHEMBOND @ 25% WT CEMENT
Adhesion to concrete (N/mm <sup>2</sup> )	0.07	2.1
Adhesion to dry steel (N/mm <sup>2</sup> )	0.0	2.0
Tensile strength	2.0	4.0
(N/mm <sup>2</sup> )	56.0	50.0
Compressive strength (N/mm <sup>2</sup> )	7.1	13.2
Flexural strength	5.2	14.3
(N/mm <sup>2</sup> )	0.0	1.9
Flexural strength after	0.07	0.01
1 year @ 70 °C (N/mm <sup>2</sup> )	46.9	4.0
Adhesion to concrete after	100	30

## Health and Safety

For all GCP products, read the product label and Safety Data Sheet (SDS) before use. Always wear PPE detailed in the SDS for this product and comply with all risk and safety phrases detailed. SDS is readily available from GCP Applied Technologies.

## Limitations

Information contained in this document does not cover all possible application scenarios or imply product suitability for an application. Please contact your local GCP representative or the GCP Technical Department for further information.

## Warranties

GCP and contractors recognised by GCP as experienced in the application of GCP products will provide warranties for individual projects. Warranty periods offered are dependent on project details and complexity. Requests for very long warranty periods may necessitate increased membrane thicknesses to ensure longevity. Contact your local GCP representative for further details.

[gcpat.com.au](http://gcpat.com.au) | Australia customer service: 1800 855 525

Australia 1800 334 444 New Zealand 0800 552 235 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898 India +91 124 402 8972 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133  
Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

CHEMBOND, MULTITEK & CRYSTALSEAL are trademarks of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2019 GCP Applied Technologies, Inc. All rights reserved.

Printed in Australia GCP PDS 058 07/17

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com.au](http://www.gcpat.com.au). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-13

[gcpat.com.au/solutions/products/chembond](http://gcpat.com.au/solutions/products/chembond)