

# MIRA® 72P

Mid-range water-reducing admixture

#### **Product Description**

 $MIRA^{**}$  72P is a water reducer specifically formulated to produce concrete with enhanced water reduction, and yield a less permeable and more durable concrete. MIRA 72P is an aqueous solution of complex organic compounds, each of which contributes uniquely to the final concrete properties.

Effective through a wide addition rate range, MIRA 72P combines the benefits of normal and mid-range water reducers allowing for the ultimate control of concrete placing and finishing properties.

MIRA 72P contains chemicals that provide improved workability and finishability to the concrete surface whilst providing air contents that are lower than conventional water reducers.

MIRA 72P is manufactured under rigid control, which provides uniform, predictable performance. It does not contain calcium chlorides, and is ready-to-use as received. Supplied as a green, low viscosity liquid, one litre weighs  $1.055 \text{kg} \pm 0.02 \text{kg}$ .

## Specification Type

MIRA 72P complies with the requirements of the following chemical admixture specifications for concrete: AS 1478 as a Type WRRe. MIRA 72P contains no Triethanolamine.

# Product Advantages

- Higher early and later age compressive strengths
- Improved concrete finishing, ideal for concrete flatwork

# **Applications**

MIRA 72P enables concrete to be produced with lower water content and improved placement properties.

MIRA 72P makes a workable mix with up to 15% less water and yields a stronger, less permeable and more durable concrete.

MIRA 72P is used in ready mix, job site, and concrete paving plants for normal and lightweight concrete and in block and precast plants. It is also effective in lean or fly ash and slag compensated mixes.





#### Chemical Action

As a dispersing agent, MIRA 72P lessens the natural inter-particle attraction between cement grains in water. It does this by colloidal action, by absorption on the cement particles, thus reducing their tendency to clump together and makes the mix more workable with less water.

As a cement catalyst, MIRA 72P also effects a more complete hydration of the cement, beginning immediately after the cement and water come together. MIRA 72P increases the gel content of the concrete, the paste or binder that "glues" the concrete aggregates together. The increased gel content adds to the water retention and internal cohesiveness of the mix, reducing bleeding and segregation as it increases workability and placeability.

#### Addition Rate

MIRA 72P will provide high water reduction with minimal extension on concrete finishing times. The amount of MIRA 72P to be used will typically range from 300 to 600mL / 100kg of cementitious material, depending upon job requirements. However, higher addition rates may be used due to variations in cement, aggregate or other job site conditions.

To assist you in obtaining optimum performance from your GCP admixtures, we offer a comprehensive advice and site assistance service backed by trained personnel, experienced in concrete and admixture technology and the facilities of our fully equipped laboratories.

Overdosing of MIRA 72P may result in extended concrete finishing times. Consult your local GCP representative if overdosing occurs.

# Compatibility with Other Admixtures

MIRA 72P is compatible with all Portland cement systems, including fly ash, slag and limestone blends. It is also compatible with all GCP admixtures currently available, but should be added to the mix separately, and not premixed with other admixtures prior to addition. Each admixture should be added to the concrete separately. MIRA 72P is compatible with LS AEA, trials are required to establish the correct dose rate.



### Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

# Packaging and Storage

MIRA 72P is available in bulk and 205 L drums. MIRA 72P contains no flammable ingredients. It will freeze at approximately 2°C but will return to full strength after thawing and thorough mechanical agitation.

# Health and Safety

See MIRA 72P Material Safety Data Sheet or consult GCP Applied Technologies.

# gcpat.com.au | Australia customer service: 1800 855 525

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

MIRA is an trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2022 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com.au. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.