

P4

Water-reducing admixture

Product Description

P4 is a liquid plasticiser or water-reducing agent used to improve workability of concrete mixes or to allow an effective reduction in the free water content to be made. The effect is achieved by its absorption onto the surface of the cement particles in a concrete mix giving a powerful deflocculating action. It can also be used to effectively reduce permeability of concrete.

P4 is formulated from carefully selected raw materials and is manufactured under controlled conditions to give a consistent product. It is based on high grade modified lignosulphonic acid derivatives and it conforms to Singapore Standard SS 320: 1987.

P4 does not contain chloride as an intentional component and is non-corrosive.

Product Advantages

- The effective plasticising action of P4 will give increased workability to most types of concrete mixes. Harsh mixes, such as those produced with crushed rock aggregates, are considerably improved in the plastic and hardened state.
- When used for its water-reducing effect, reductions in the water content in the region of 10% can normally be achieved with subsequent increases in strength, impermeability and durability.
- P4 can be used to modify concrete mix designs to achieve cement reductions.
- The reduction in excess water which can be achieved, together with the slight air entrainment, characteristic of lignosulphonic acid derivatives, is effective in increasing the impermeability of concrete. Surface finishes can be improved and blemishes such as 'sand runs' overcome.
- P4 is of particular value in concreting operations subject to high ambient temperatures.
- It extends the period of time when the concrete can be placed and compacted.
- P4 is recommended for use where waterproofing of structural concrete is specified. Significant reductions in water permeability and penetration can be obtained.

Typical Properties

Appearance: Dark brown liquid

Specific Gravity: 1.195kg ± 0.02kg

Air Entrainment: Air content of concrete mixes will normally be increased by between 1% and 2%

Compatibility With Cements

P4 can be used with all types of Portland, Pozzolanic and Blast Furnace cement. It is also compatible with cements containing fly ash and microsilica.

Compatibility With Other Admixtures

P4 should not be premixed with other admixtures. The performance of the material may be affected by the presence of other chemicals. It is advisable to add all admixtures separately to a cementitious mix.

Method of Use

P4 is supplied ready for use. It should be added to concrete mixes during the mixing process, at the same time as the water or the aggregates. It should not be added directly to the cement. No extension of normal mixing time is necessary.

Dosage Rates

Range: 280mL to 850mL / 100kg of cementitious material.

The performance of P4 is best assessed after preliminary tests on site, using the actual concrete under consideration to determine the optimum dosage and effect on concrete properties such as ultimate compressive strength, early rate of gain of strength and shrinkage, when these are of consequence.

As a guide to these trials, dosage of 400mL - 850mL / 100kg cement is recommended.

Effects of Overdosing

Overdosing of P4 will generally produce a considerable increase in workability and in certain circumstances, a slight increase in air entrainment. This particularly in cold weather, will be accompanied by a retardation of the initial and final set of the concrete. In such cases, however, provided the concrete is properly cured, the ultimate strength will generally be higher than for normal concrete. The effects of overdosing will be exaggerated when sulphate-resisting cement is used in place of ordinary Portland Cement.

Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

Packaging

P4 is supplied in 205L drums or bulk deliveries can be arranged.

Storage

P4 should preferably be stored in sealed conventional containers and protected from the elements.

Storage Life in Manufacturer's Drums:

12 months from date of manufacture

Bulk Storage:

12 months from date of delivery

Health and Safety

For further information see the P4 Material Safety Data Sheet, or consult GCP Applied Technologies.

gcpat.com.au | Australia customer service: 1800 855 525

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

© Copyright 2018 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com.au. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-07-06

gcpat.com.au/solutions/products/p4