

SILCOR[®] 560 HB

Class III high-build polyurethane waterproofing membrane

Product Description

An economical, one-part, liquid applied, high solids polyurethane waterproofing membrane.

SILCOR[®] 560 HB is a “Class III – High Extensibility” membrane for use in internal and external applications. Formulated for simple application to horizontal or vertical substrates, the product cures through reaction with humidity and forms a robust, flexible membrane.

Product Uses

SILCOR 560 HB is intended for installation as a non-exposed Class III External Above Ground membrane or Class III Internal Wet Area floor membrane.

SILCOR 560 HB may be used in non-exposed applications where membrane is fully covered by an overlay. It is unsuitable for exposed, trafficable or non-trafficable applications (with the exception of upturns).

Typical applications include external, non-exposed areas, such as:

- Balconies, roof tops and decks (under screed & bedded pavers or screed & tiles)
- Balconies, roof tops and decks (under drainage cell, insulation and / or ballast)
- Balconies, roof tops and decks (under pods & pavers with top coat protection)
- Planter boxes, green roofs, and landscaped decks
- Retaining walls and lift pit walls
- Window / door rebates and reveals

and internal wet area floors under or over screeds in:

- Bathrooms and toilets
- Showers and shower rooms
- Laundries
- Kitchens

Advantages & Features

- Certified Class III – compliant with AS 4654.1-2012 for use as external, non-exposed waterproofing, installed to the requirements of AS 4654.2-2012
- Certified Class III – compliant with AS/NZS 4858-2004 for use as internal wet area waterproofing, installed to the requirements of AS 3740-2021
- Low VOC – <110g/L – reduced EH&S issues on site
- High physical properties; >700% elongation and >3MPa tensile strength
- Seamless – liquid applied and monolithic, eliminating vulnerable joins, seams, and laps
- High build – suitable for vertical and horizontal application

- Fully Bonded – no water tracking between membrane and substrate
- Simple Application – one-part, humidity cured. Applied by roller or brush
- Cold Applied – no flame or heat required for application
- Accommodates typical structural movements encountered in well-designed construction
- Bridges non-structural concrete shrinkage cracks
- Polyurethane chemistry – free from bitumen or tar – will not bleed or stain

Product Properties

PROPERTY	TYPICAL VALUE	TEST METHOD
Liquid Membrane Properties		
Membrane Chemistry	High solids, moisture curing polyurethane	
Appearance	Charcoal grey viscous liquid	
Specific Gravity ¹ (g/ml)	1.48	
Brookfield Viscosity (mPa.s)	60,000	
Solids Content (%w/w)	91	
VOC (g/L)	<110	ASTM D3960
Tack Free Time ¹ (hours)	4	
Gel Time ¹ (hours)	6	
Min. Recoat Time ¹ (hours)	12	
Max. Recoat Time ¹ (hours)	48	
Min. Through Cure Time ¹ (hours)	48	
Min. Cure Time ¹ (hours)	2	
Rain resistant		
Min. Cure Time ¹ (hours)	48	
Ready for flood testing, topping or backfilling		
Fully Cured Membrane Properties		
Shore A Hardness (°A)	> 55	ASTM D2240
Tensile Strength (MPa)	> 5.0 / >3.0	AS 4858 / AS 4654.1
Elongation (%)	> 1400 / > 700	AS 4858 / AS 4654.1
Classification	Class III High Extensibility – AS 4858-2004 Class III High Extensibility – AS 4654.1-2012	AS 4858 / AS 4654.1
Resistance to Cyclic Movement	Pass / Pass – No fatigue cracking exhibited	AS 4858 / AS 4654.1
Bond Strength to Primed Concrete (N)	>56	AS 4654.1
Water Vapour Transmission Rate (g/m ² /24h)	4.36 / 4.36	AS 4858 / AS 4654.1

Resistance to Water Immersion	Pass / Pass	AS 4858 / AS 4654.1
Resistance to Bleach Immersion	Pass	AS 4858
Resistance to Detergent Immersion	Pass / Pass	AS 4858 / AS 4654.1
Resistance to Heat Ageing	Pass / Pass	AS 4858 / AS 4654.1

The above values and properties do not constitute a specification.

1 – Tested at 23°C / 60% RH. Values will vary dependent on temperature and/or humidity at time of use.

Design

- All horizontal substrates to have a minimum 1:100 fall to drainage and/or not retain water other than residual due to substrate surface tension. Falls to drainage in shower areas to be minimum 1:80.
- Drainage outlets / puddle flanges must be at low point of falls, installed flush or recessed to surrounding substrate.
- Drainage outlets must allow correct drainage both below and above screeds. Consult your GCP representative for specific requirements on your project.
- All membrane under pods & pavers, regardless of paver gap width and turn-ups above or below finished paver surface must receive SILCOR® Top Coat 75 or other membrane UV protection.
- Where bonded screeds, renders, bedded pavers or direct stick tiles are to be installed to SILCOR 560 HB membrane, a tie coat must be installed to the cured membrane prior, consisting of an additional layer of SILCOR® 575 HB membrane (not SILCOR 560 HB), coarse aggregate blinded to refusal. See details below for further information.
Note – aggregate broadcasting of the finished membrane (without incorporating the tie coat) is unacceptable.

Safety and Handling

- Installers must read and understand the product label and Safety Data Sheet (SDS) for each product.
- All users should acquaint themselves with this information prior to working with the products and follow the precautionary statements.
- SDSs can be obtained by contacting your local GCP representative or office.

Packaging

SILCOR® 560 HB is supplied in 22kg pail.

Storage & Shelf Life

- Store in original packaging between 15° and 25°C, under cover and protected from all sources of heat, ignition, moisture, frost and direct sunlight.
- Shelf life is 9 months from date of manufacture when stored at these conditions in original, unopened packaging.

Limitations of Use

- Minimum applied membrane thickness required is specified by GCP and is dependent on intended areas of use and Product Warranty period desired. Consult your local GCP representative for further information
- Not recommended for exposed non-trafficable or trafficable areas, with or without protective top coat over, with the exception of membrane turn-ups above finished surfacing
- Not to be installed as a negative pressure membrane
- Not to be installed to damp, wet, contaminated or unprepared substrates
- Not recommended for internal lining of water tanks
- Must not be applied if it is raining or rain is imminent
- Not to be installed when ambient humidity is below 35% or above 85%
- Cure rate, drying time, recoat time etc are affected by temperature and humidity:
 - High temperatures and/or high humidity will accelerate surface skinning and cure time
 - Low temperatures and/or low humidity will extend cure time
- Information in this document does not cover all possible application scenarios, limitations, or imply product suitability for an application. Please contact your local GCP representative for further information and to discuss your requirements prior to proceeding with installation
- This PDS does not constitute a GCP Product Specification, Work Method Statement or Scope of Works. Please contact your local GCP representative for project specific installation information

System Components

PRODUCT	DESCRIPTION	PACKAGE SIZE
SILCOR® 560 HB	1-part, high solids, polyurethane waterproofing membrane	22 kg pail
SILCOR® Primer BS	1-part, penetrating solvent-based polyurethane primer for dry concrete, masonry, CFC sheet, CCS, many metals, PVC and ABS plastics	17 kg pail
EPOCOTE™ F100W	2-part, water-based epoxy primer for dry, green or damp concrete, masonry, CFC sheet, water resistant plasterboard, many metals, PVC and ABS plastics	20 L kit
SILCOR® LM PU Sealant	1-part, low modulus polyurethane sealant for detailing	600 ml foil sausage
SILCOR® Top Coat 75	2-part, membrane protective, aliphatic polyurethane top coat	18 kg kit
PROTECTOBOARD™	High crush strength, fluted polypropylene, membrane protection board	1830 x 1220 x 3mm sheet
RAPID-DRAIN™	High crush strength, dimpled polypropylene, drainage and membrane protection board	15240 x 1220 x 10mm roll

Estimating

Please contact your local GCP representative for information specific to your project estimating needs.

General Guidance:

MINIMUM TOTAL DFT (MM)	MINIMUM TOTAL WFT (MM)	MAXIMUM TOTAL APPLICATION RATE (KG/M ²)	MAXIMUM TOTAL APPLICATION RATE (M ² /LITRE)	NUMBER OF COATS	MINIMUM DFT PER COAT (MM)	MINIMUM WFT PER COAT (MM)	APPLICATION RATE PER COAT (KG/M ²)	APPLICATION RATE PER COAT (M ² /LITRE)	MAXIMUM COVERAGE PER PAIL (M ²)
External Above Ground Areas – AS 4654.1									
1.35	1.48	2.18	0.68	2	0.68	0.74	1.09	1.36	10.08
1.75	1.91	2.83	0.52	2	0.88	0.96	1.41	1.05	7.78
Internal Wet Areas – AS 4858									
1.35	1.48	2.18	0.68	2	0.68	0.74	1.09	1.36	10.08
1.75	1.91	2.83	0.52	2	0.88	0.96	1.41	1.05	7.78
Note – The above values do not include wastage.									

Suitable Substrates

SILCOR 560 HB may be applied to the following dry, cured, stable, prepared & primed substrates:

- Concrete or reinforced and core filled blockwork with compressive strength ≥ 20 MPa
- Cementitious screed, render or toppings with compressive strength ≥ 20 MPa
- Engineered screeds with compressive strength ≥ 25 MPa
- Compressed Fibre Cement sheet (CFC), Cement Composite Sheet (CCS)
- Water resistant plasterboard, water resistant plywood or water-resistant structural timber
- Many types of metals, PVC, and ABS plastics
- High strength rendered, aerated autoclaved concrete (AAC)

Substrate Quality

Substrates must be structurally sound, smooth, clean and dry.

Concrete

- Well compacted, moisture cured as required by AS 3600
- Minimum concrete age = 14–28 days, dependent on concrete thickness, moisture content and primer
- Compressive strength – minimum strength grade 20 MPa
- Concrete surface pull-off strength – minimum 0.6 MPa for internal wet area applications; minimum 1.0 MPa for external surfaces
- Concrete finish – only steel trowel, light power float or off-form, well compacted (not burnished), free of honeycombing, voids or excessive porosity. Porous, low surface strength, tamped, bull float or broom finishes are unacceptable and must be rectified prior to primer and membrane application. Where non-ponding external surfaces are specified, in accordance with AS 4654.2, concrete provided to the applicator shall be set to falls and be free of ponding depressions.
- Curing compounds – only non-permanent, degrading acrylic types. Must be removed by water blasting or grinding prior to priming

Concrete Block Masonry

- Sound, flush pointed mortar joints with no gaps or voids, reinforced and fully core filled. Excessively porous block work may require sealing with high strength (minimum 20 MPa) fairing compound prior to primer and membrane application

Screeds, Toppings and Renders

- Structurally sound, fit for purpose, minimum 20 MPa compressive strength grade and reinforced or resistant to fracture or break-up in use. Formulated, mixed and installed to provide a smooth surface without voids or excessive porosity. Minimum 3 days cure dependent on formulation, moisture content and GCP primer being used

Compressed Fibre Cement (CFC) Cement Composite Sheet (CCS) & W/R Plasterboard

- Installed to stable, structural framing. Installed and finished in accordance with manufacturer's directions. Free of all surface sealers, coatings, and primers

Metals

- Free of corrosion, gaps, holes and defects

Substrate Preparation

Concrete, Masonry, Screeds and Renders

- Remove all dirt, dust, concrete spillage, weak material, laitance, oil, grease, coatings, curing compounds, form release agents, rubber tyre marks, rain damage, corrosion marks and other contaminants / defects by an appropriate method, including brooming, vacuuming, scraping, water blasting (4000 psi with RotorJet head), captive shot blasting or grinding
- Remove ridges, sharp edges, deep broom finishes and chamfer external corners 12mm
- Repair concrete masonry defects including bug holes, honeycombing and gross pin holing using a low shrinkage PMC repair mortar, fairing compound or epoxy repair mortar, having equivalent compressive strength as the substrate. Allow all repairs to cure fully and dry to a moisture content below the maximum allowable for the GCP primer being used (see relevant primer PDS)
- Chase construction joints minimum 10mm x 10mm (square cut only). Chase static shrinkage cracks greater than 1.0mm width a minimum 6mm x 6mm (square cut recommended). All structural and dynamic cracks must be repaired by suitable means prior to chasing

Note – Outgassing occurs naturally in concrete and masonry surfaces as daily temperature increases and can lead to pin hole formation in applied primers, membranes, and coatings. Rectification of rain damaged or burnished concrete by grinding or sand blasting can expose high porosity concrete, leading to increased outgassing. The applicator must assess the prepared substrate for porosity and adjust repair and priming methods accordingly to minimise the effects of outgassing and pin hole formation in primers and membranes.

Compressed Fibre Cement Sheet (CFC)

Ensure sheeting materials used are free of all surface sealers, coatings and acrylic primers.

Ensure sheets have been installed to the manufacturer's requirements, and are clean, dry and contaminant free.

Light Weight Cement Composite Sheet (CCS)

In addition to CFC sheet requirements, due to laminar structure and low internal strength of CCS sheets, they must be prepared and primed carefully using a very low viscosity, high penetration GCP primer such as SILCOR Primer BS, only.

Metals

Remove all dirt, dust, oil, grease, corrosion and oxides from steel, aluminium, zinc/galvanising, copper, stainless steel etc. and roughen surface by abrasion or garnet blasting to SA 2.5 near white metal. Solvent wipe with clean xylene or methyl ethyl ketone (MEK) on a clean, lint free cloth. Prime surface within 30 minutes to minimize surface oxidation.

Plastics

Remove all dirt, dust, oil, grease and other contaminants.

For PVC, epoxy, polyester and ABS, solvent wipe with MEK solvent immediately prior to priming.

For difficult to bond plastics such as HDPE or PP, consult the GCP Technical Department before proceeding.

Aerated Autoclaved Concrete (AAC)

Surface must be high-strength rendered to seal and provide a strong, smooth finish. Allow render to dry to a moisture content below the maximum allowable for the GCP primer being used (see relevant primer PDS).

Detailing

Internal Wet Areas

- Detail according to NCC and AS 3740-2021 requirements, by installing minimum 12mm x 12mm bond breaker fillets of SILCOR® LM PU Sealant to all internal corners. Detail and seal penetrations, drainage outlets etc.
- Allow sealant to cure a minimum 12 hours

External Above Ground Areas

- Detail according to NCC and AS 4654.2-2012 requirements, by installing minimum 15mm x 15mm bond breaker fillets of SILCOR LM PU Sealant low modulus polyurethane sealant to all internal corners and around penetrations. Detail and seal drainage outlets etc.
- Allow sealant to cure a minimum 12 hours

Expansion Joints

- Consult your local GCP representative for further information

Chased Non-Moving Construction Joints & Shrinkage Cracks

- Install bond breaker tape to base of primed square cut chases. Gun SILCOR LM PU Sealant to chase and tool to a smooth concave finish
- Allow sealant to cure a minimum 12 hours

CFC & Cement Composite Sheet Joints

- Ensure sheet joints are detailed per the manufacturer's directions

Priming

General

- Prime all substrates with an appropriate GCP primer prior to applying SILCOR 560 HB membrane
- Application to porous substrates while substrate temperature is increasing may result in substrate outgassing and pin-hole formation in primer, leading to pin-hole formation in the membrane. This can be reduced or prevented by priming substrates when the substrate temperature is stable or falling
- The applicator must ensure primed substrate is pin-hole free prior to membrane application
- Adjust application procedures and schedule to suit local conditions
- Membranes must be applied to the primed surface within the primer recoat window. Consult the relevant primer PDS for further details. If recoat time of primer is likely to be exceeded, broadcast the freshly applied primer with clean, kiln dried, sharp quartz sand of 0.5 to 1.0mm diameter to 120% coverage (to refusal). Allow primer to cure completely and remove excess loose sand by vacuuming. Membrane may be applied to the sand blinded surface up to 14 days after laying, provided the surface remains clean, dry and free of all contamination.

Primer Selection – Below 5.0% Moisture Content

- Prime substrates using SILCOR® Primer BS or EPOCOTE™ F100W Clear
- For highly porous, damaged or old concrete and masonry, prime with EPOCOTE F100W Grey
- For greatest penetration and adhesion to CCS flooring substrates (Scyon Secura, CSR Cemintel etc), SILCOR Primer BS is recommended
- For metals, PVC, ABS and other non-porous substrates, use EPOCOTE F100W Clear or SILCOR Primer BS
- Coverage rate is dependent on surface porosity and may require two or more applications
- Consult the relevant primer PDS for further application information and application rate
- For difficult to bond metals such as stainless steel, copper, and aluminium, prepare, clean, then wipe on Dow Chemical DOWSIL 1200 OS Primer per the manufacturer's directions, then apply membrane directly

Primer Selection – 5.0% to 6.9% Moisture Content

- Prime prepared concrete and masonry substrates using only EPOCOTE F100W Clear or allow substrates to dry <5.0%. Note 6.9% is the upper limit for testing surface moisture content using commercially available test equipment calibrated for concrete testing.

Membrane Application

General

Ensure the following parameters are met before and during membrane application and cure:

PARAMETER	LIMITS
Substrate Temperature	+5 °C to +35 °C (temperature stable or falling is recommended)
Ambient Temperature	+5 °C to +35 °C
Relative Humidity	35% to 85%

Dew Point	Minimum 3 °C below substrate temperature
Condition	Clean, dry and free from condensation, contaminants, stones, leaves, debris etc.

Application Equipment

SILCOR 560 HB membrane is best applied in two cross directional applications by 10–14mm nap, non-shedding roller or brush.

Mixing

Mix material thoroughly before use using a minimum 650W, variable speed drill (maximum 600 RPM) fitted with a clean paddle or “Jiffy” type mixer. Avoid entraining air into the product during mixing.

Applied Membrane Thickness Control

Apply membrane at or above the minimum required thickness, as detailed in the GCP Project Specification. Product must be installed at the correct and specified Dry Film Thickness (DFT). Consult your GCP Specification for the project or contact your representative for further details.

To ensure correct DFT is installed, test applied thickness during application using a clean, accurate Wet Film Thickness (WFT) gauge and adjust applied thickness of liquid membrane accordingly. Test WFT regularly, typically every 2m² (0.5m² to 1m² for small areas).

Horizontal, Vertical or Sloping Application

SILCOR 560 HB is suitable for horizontal, vertical, and sloping applications. Note this product is not self-levelling. Two or more coats are typically required to achieve the required DFT. One coat application may be employed, however full through cure time will be significantly extended.

Applied Membrane Appearance

Application by roller or brush typically produces a textured surface finish.

Movement Areas

At potential movement areas such as detailed and sealed expansion joints, construction joints and active cracks, install a bond breaker tape centred over the joint or crack. Bond breaker tape should be a minimum 90mm wide for expansion joints, minimum 45mm wide for construction joints and minimum 20mm wide for moving cracks.

Bond breaker tape must be flexible, polyethylene faced, single sided adhesive and resistant to primer, membrane, xylene and heat (90 °C or greater). Tape must be less than 0.5mm thickness. Adhesive must be natural rubber or butyl rubber based. Suitable tapes are 3M 8979 or Tesa 58663.

Reinforcing

Full reinforcing of SILCOR 560 HB is not typically recommended, provided the membrane is applied to the minimum specified WFT/DFT. Where high movement is expected at junctions and joints and use of a bond breaker tape is not possible, a reinforcing strip may be employed, as detailed in Membrane Detailing below.

Membrane Detailing

- To SILCOR LM PU Sealant detailed internal corners, penetrations, drainage outlets, cracks, to chamfered external corners and to bond breaker taped construction joints and cracks, apply SILCOR 560 HB as a minimum 150mm wide application centred over the sealant fillet/corner/bond breaker tape. Apply to provide a minimum 1.0mm DFT (1.1mm WFT) and allow to cure to minimum recoat time.
- To the SILCOR LM PU Sealant detailed expansion joints, apply SILCOR 560 HB as a minimum 200mm wide application centred over the joint bond breaker tape. Apply to provide a minimum 1.0mm DFT (1.1mm WFT) and allow to cure to minimum recoat time.

Where reinforced membrane is required in high movement areas, without bond breaker tape, the following process is recommended to ensure correct membrane function:

- Apply SILCOR 560 HB to a minimum 1.0mm DFT (1.1mm WFT) as detailed above and allow to cure to minimum recoat time.
- Apply a second coat of membrane and lay Reinforcing PE Fabric strip into the wet membrane. Wet fabric through with membrane completely, ensuring no bubbles or wrinkles are present.
- While wet, apply additional membrane to fully cover the reinforcing fabric with a minimum 1.0mm WFT of membrane. Allow to cure to minimum recoat time.
- Use only GCP's Reinforcing PE Fabric as reinforcing. Do not use fibreglass chopped strand mat or other reinforcing materials.
- Reinforce using the step wise method shown in i) to iii) above. Do not use a one-step wet-on-wet reinforcing method.

Application of Continuous Membrane

- Within the recoat window of the primer used, apply SILCOR 560 HB membrane to detailed and primed areas, at or above the required minimum thickness in two (or more) cross directional coats
- Required minimum thickness is dependent on installation area, type of use of the area, membrane surfacing being employed, and product warranty period required and will be specified in the GCP Waterproofing Specification. Contact your local representative to obtain a GCP Waterproofing Specification for your project. Where not specified, a minimum DFT of 1.5mm must be employed.
- Ensure good airflow in the application area for fastest membrane drying time
- Allow to dry fully between coats. Test WFT during application using a WFT gauge and adjust applied thickness accordingly
- Continue membrane to turn-ups by a minimum 100mm above finished surface level, or as detailed in project specification or AS 4654.2-2012, whichever is greater

Typical Membrane Cure & Recoat Times

AMBIENT OR SUBSTRATE TEMPERATURE (°C)	TACK FREE TIME (HRS)	MINIMUM RECOAT TIME (HRS)	MAXIMUM RECOAT TIME (HRS)	READY FOR FLOOD TESTING OR TILING (HRS)
35	3	8	36	36
30	3.5	10	40	40

23	4	12	48	48
15	8	16	60	60
10	15	22	80	80
5	24	30	100	100

Note – Above times are based on 60% RH (Relative Humidity) during application and cure. Times will increase at lower RH; times may decrease with higher RH.

Clean-up

Clean equipment immediately using xylene solvent. Cured product must be removed mechanically.

Protection and Surfacing

SILCOR 560 HB must be permanently protected from damage, abuse, and wear by one of the following:

Top Coat to Exposed Non-Trafficable Membrane Turn-Ups

- Mix and apply SILCOR Top Coat 75 to exposed membrane turn-ups as a minimum two cross-directional coats and a minimum rate of 0.15kg/m²/coat. SILCOR Top Coat 75 contains an in-built slip resistance aggregate, making accurate measurement of applied film DFT or WFT difficult. Application rate of 0.15kg/m²/coat is approximately equal to a DFT of 83 micron/coat (165 micron for two coats) and a WFT of 135 micron/coat (270 micron for two coats)
- Consult the PDS for SILCOR Top Coat 75 for installation information

Top Coat to Semi-Exposed Membrane Under Pavers on Pods or Timber Decking

- SILCOR 560 HB is compatible with pavers on pods/adjustable jacks or timber decking on framework
- Pods / jacks used should have a flat base with minimum footprint size of 150mm diameter to prevent point load damage to membrane.
- Regardless of paver / decking gap width, all membrane (above and below pavers / decking) must be protected by two cross-directional coats of SILCOR Top Coat 75 applied at minimum 0.15kg/m²/coat or a UV light blocking layer such as heavy geotextile, PROTECTOBOARD etc.

Unbonded Screeds and Topping Slabs

- Install PROTECTOBOARD™ or two layers of minimum 250 micron builder's plastic to the cured membrane as a slip sheet prior to installing screed or topping slab. Ensure all protection board/sheet laps are taped to seal

Direct Stick Pavers, Tiles, Bonded Screed or Bonded Topping Slab

Membrane surface must be compatibilized before application of cementitious tile adhesives, bonded screed or topping slab as follows:

- Between 12 and 48 hours of final membrane application, lightly solvent wipe the membrane surface using isopropanol. Allow to dry, then apply a coat of SILCOR 575 HB or SILCOR 575 LB (not SILCOR 560 HB) membrane at a rate of 0.95 kg/ m² (WFT=0.6mm). Broadcast the freshly applied membrane with clean, kiln dried, sharp quartz sand of 0.5 to 1.0mm diameter to 120% coverage (to refusal). Allow membrane to cure at least 24 hours and remove excess loose sand by vacuuming. Membrane must not be visible through the sand cover.
- Tiles may be applied using high quality polymer modified cementitious tile adhesives.
- Screeds and topping slabs should be polymer modified, or have a minimum 20 MPa compressive strength, to resist break-up in use.

Backfill

- Install PROTECTOBOARD or RAPID-DRAIN™ to membrane as protection and/or drainage prior to backfilling with graded fill or filling of planters with soil.
Where non-graded fill is to be used, install PROTECTOBOARD™ HS or high compressive strength drainage cell as protection.

Landscaping

- Install PROTECTOBOARD or RAPID-DRAIN membrane protection prior to backfilling with soil / planting media
- Install PROTECTOBOARD, RAPID-DRAIN, heavy-duty drainage cell or heavy-duty needle punched geotextile (minimum 500gsm) over the cured membrane as protection and/or drainage prior to soil loading.
- Where certified root resistance is specified, install a certified, 3rd party root barrier prior to backfilling with soil / planting media

Pebble Ballast

Install RAPID-DRAIN drainage cell over membrane to protect and ensure free drainage to falls prior to loading of pebble ballast. Ballast must be hand loaded with care to prevent damage to drainage cell or and membrane.

Insulation and Ballast

Install foam sheet insulation over RAPID-DRAIN to ensure free drainage to falls. Cover insulation with geofabric prior to loading of pebble ballast.

Maintenance

- Not typically required for non-exposed, covered membrane.
- For exposed top coated membrane turn-up areas, regular cleaning and inspection maintenance is required per the relevant GCP Operation and Maintenance manual for polyurethane membranes and top coats.

Product Warranties

- GCP will provide to the purchaser a product warranty for qualified individual projects on request.
- Contractors recognised by GCP as trained and experienced in the application of GCP products will provide installation warranties for equivalent time periods.
- GCP Product Warranty periods offered and minimum applied DFT required for that warranty period are dependent on project details and complexity. Contact your local GCP representative for specific requirements and a GCP Specification, before commencing waterproofing installation on your project.

gcpat.com.au | Australia customer service: 1800 334 444 – anzorders@gcpat.com

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

EPOCOTE, PROTECTOBOARD RAPID-DRAIN and SILCOR are trademarks trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2025 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com.au. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-06-23

gcpat.com.au/solutions/products/silcor-liquid-waterproofing/silcor-560-hb