

V-MAR[®] 4

Rheology-modifying admixture for self-consolidating concrete

Product Description

V-MAR[®]4 is a high efficiency, liquid admixture designed to enable production of Self-Consolidating Concrete (SCC) by modifying the rheology of concrete. V-MAR 4 works by increasing the viscosity of the concrete while still allowing the concrete to flow without segregation. V-MAR 4 is based on a unique, patented biopolymer and is manufactured under closely controlled conditions to provide uniform, predictable performance.

V-MAR 4 complies to AS 1478 as a Type SN admixture. V-MAR 4 admixture is supplied as a ready- to-use milky white liquid. One litre weighs approximately 1.02kg. V-MAR 4 contains no intentionally added chlorides.

Product Advantages

SCC produced with V-MAR 4 has unique advantages over conventional flowing concrete:

- Self Placement: Vibration can be eliminated because SCC is highly flowable and will change shape under its own weight to self level and self consolidate within formwork.
- No Segregation: SCC is a flowable yet highly cohesive material that will not segregate, and has significantly reduced bleeding.
- No Blocking: SCC can pass freely through narrow openings and congested reinforcement without aggregate “blocking” behind obstructions that stop the flow of concrete.

V-MAR 4 is an easy-to-dispense liquid admixture. Dosage rates can be adjusted to meet a wide spectrum of SCC performance requirements.

Uses

V-MAR 4 is recommended for use in conjunction with ADVA[®] superplasticisers to produce SCC.

V-MAR 4 is recommended for use in precast and prestressed concrete.

V-MAR 4 enhances the ability to manufacture SCC by allowing for variations in aggregate gradations and moisture contents. This can greatly reduce the time required to develop SCC mixes, and time required to update and test new mix designs if raw materials change. In addition, V-MAR 4 allows for the production of SCC in applications where mix designs and materials can not be modified for SCC properties, such as exposed aggregate concrete.



Benefits

SCC produced with V-MAR 4 and ADVA superplasticisers is designed to eliminate the need for vibration and manual compaction in precast and cast-in-place concrete.

For precast/prestressed concrete producers SCC provides the following benefits:

- Reduced labour and improved productivity through faster and easier concrete placement with no vibration.
- Eliminated/reduced the need for surface touch ups to yield the highest quality surface finish,
- Improved labour safety, reduced plant noise levels and improved work environment.
- Reduced wear and tear on forms by eliminating vibration.
- Achievement of complete consolidation throughout concrete elements, even in thin walled, highly reinforced units.
- Increased production flexibility by enabling use of form geometry and form orientations in which placement of conventional concrete mixes would be difficult or impossible.

Addition Rates

V-MAR 4 is typically used at an addition rate of 500 to 2,000 mL / m³ of concrete.

Dosage requirements are based on water content in the mix. As water content increases, the V-MAR 4 requirement will increase. Typical water contents for SCC mixes are 165 to 190L / m³. At lower water content, use V-MAR 4 at the lower dosage range, at higher water content, dosage rates will be higher.

V-MAR 4 dosage requirements may also be affected by mix design, cementitious content, aggregate gradations and SCC application. Please consult with your local GCP representative for more information and assistance.

ADVA series of superplasticisers is highly recommended for use in SCC production. Dosage rate requirements for superplasticisers are typically slightly higher for SCC than for conventional concrete mixes.

Pre-placement testing is recommended to determine the optimum admixture addition rate. Factors that influence optimum addition rate include other concrete mix components, aggregate gradations, form geometry, and reinforcement configurations. Please consult your local GCP representative for assistance with developing mix designs, admixture combinations and SCC production.

Compatibility with Other Admixtures

V-MAR 4 can be used to make SCC with all ADVA superplasticisers, i.e. ADVA CAST 640, ADVA 650 and ADVA Cast 630. V-MAR 4 is compatible with all WRDA[®] PC-based water reducers, retarders and MIRA[®] mid-range water reducers. Each admixture is to be added separately to a mix.

Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

Packaging

V-MAR 4 is available in bulk, drums and pails. It will freeze at about -2°C but will return to full functionality after thawing and thorough mechanical agitation.

Health and Safety

Read and understand the product label and Safety Data Sheet (SDS). All users should acquaint themselves with this information prior to working with the products and follow the precautionary statements. SDSs can be obtained by contacting your local GCP representative or office.

gcpat.com.au | Australia customer service: 1800 855 525

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

V-MAR, ADVA, WRDA and MIRA are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebald Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com.au. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-07-06

gcpat.com.au/solutions/products/v-mar-admixtures/v-mar-4