

# V-MAR<sup>®</sup> 6

Rheology-modifying and mix-enhancing admixture

---

## Product Description

V-MAR<sup>®</sup>6 is a rheology-modifying and mix-enhancing admixture that can be used in a variety of concrete mixes. V-MAR<sup>®</sup>6 is based on a high molecular weight polymer that is designed to improve cohesion, flow, lubricity and “softness” to concrete. V-MAR<sup>®</sup>6 complies to AS 1478.1 as a Type SN.

## Product Advantages

- Using suitable mix designs, self-compacting concrete (SCC) produced with V-MAR<sup>®</sup> 6 flows and consolidates around reinforcement without blocking or segregation.
- V-MAR<sup>®</sup> 6 is a workability/pumpability-enhancing admixture which reduces friction within a concrete mix, making placing, screeding, pumping and finishing much easier. V-MAR<sup>®</sup> 6 used in the correct mix can also assist in minimising bleed.
- Self-consolidating concrete SCC produced with V-MAR<sup>®</sup> 6 is especially suitable for large scale civil engineering application as it has neutral setting time and high early strength, allowing rapid progress to be achieved.
- V-MAR<sup>®</sup> 6 may also be considered in spray/shotcrete mixes to reduce or eliminate the amount of silica fume required.

## Compatibility with Cements

V-MAR<sup>®</sup>6 can be used with all types of Portland Cements and it is effective in concretes containing pulverised fly ash and/or ground granulated blast furnace slag. For use with special cements we recommend that you consult your local GCP representative..

## Compatibility With Other Admixtures

V-MAR<sup>®</sup>6 should not be premixed with other admixtures. The performance of the material may be affected by the presence of other chemicals and we would recommend that GCP be consulted in such circumstances.

## Method of Use

V-MAR<sup>®</sup>6 is supplied ready to use. When producing high workability concrete, V-MAR<sup>®</sup>6 should be added “up-front” with part of the batching water. An ADVA<sup>®</sup>Superplasticiser to be added after the V-MAR<sup>®</sup>6 has been discharged, i.e with the last 20–25% of batch water.

When used in “non-SCC type concretes” V-MAR<sup>®</sup>6 should be added “up-front” with the initial part of mix water followed by other admixtures.

## Addition Rates

For SCC type concretes and as a silica fume part replacement, dose range is 3 to 5L per m<sup>3</sup>. For “non-SCC” concretes V-MAR<sup>®</sup>6 can be used at 500 to 1,000mL / m<sup>3</sup>.

As with most products of this type, the magnitude of the effect obtained with V-MAR<sup>®</sup>6 is governed by the quantity of product used, water-cementitious ratio, and the specific nature of concrete and its constituent materials.

It is necessary therefore to assess performance under site conditions using site materials to determine optimum dosage and effect on both plastic and hardened concrete properties, such as cohesiveness, workability retention, set characteristics, early rate of strength gain, ultimate compressive strength and shrinkage when these are of consequence. For advice and assistance with your trials we would recommend that you consult your local GCP representative.

## Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

## Packaging

V-MAR<sup>®</sup>6 is supplied in 205L drum and 1,000L tote-tanks.

V-MAR<sup>®</sup>6 should preferably be stored protected from frost. If the product does become frozen, it should be carefully mixed after thawing out to restore it to its normal state.

## Health and Safety

V-MAR<sup>®</sup>6 is formulated from chemicals which present no fire or health hazards. If, however, it is spilled, the floor will be made slippery and should be washed down immediately with cold water. For further information, see V-MAR<sup>®</sup>6 Material Safety Data Sheet, or consult GCP Applied Technologies.

[gcpat.com.au](http://gcpat.com.au) | Australia customer service: 1800 855 525

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

V-MAR and ADVA are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com.au](http://www.gcpat.com.au). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-07-06

[gcpat.com.au/solutions/products/v-mar-admixtures/v-mar-6](http://gcpat.com.au/solutions/products/v-mar-admixtures/v-mar-6)